

No.: QDIN2206003832SC

Date: Jul 06, 2022

Page: 1 of 4



CUSTOMER NAME: QINGDAO POWERWING BOAT EQUIPMENT CO., LTD.

ADDRESS: 706 IKEA KASO BUILDING, 100 SHENZHEN ROAD, LAOSHAN

DISTRICT, QINGDAO, CHINA 266061

Sample Name : Boat Propeller

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Date of Receipt : Jun 30, 2022
Testing Start Date : Jun 30, 2022
Testing End Date : Jul 06, 2022

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services (Qingdao) Co., Ltd.

Kayla Chu

Authorized signatory

Xayla Chu





No.: QDIN2206003832SC

Date: Jul 06, 2022

Page: 2 of 4

Summary of Results:


No.	Test Item	Test Method	Result	Conclusion
1	Neutral Salt Spray Test	ISO 9227:2017	Appearance rating: 10	Pass

Note: Pass: Meet the requirements;

Fail: Does not meet the requirements;

/: Not Apply to the judgment.

Original Sample Photo:





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overleaf, available on request or accessible at http://www.sgs.com/en/ferms-and-Conditions.apxx.and, for electronic format document subject to Terms and Conditions for Electronic Documents at https://www.sgs.com/en/ferms-and-Conditions/ferms-e-Document.apx. Attention is drawn to the limitation of liability, indemplication and jurisdiction issues defined therein. Any holder of his document advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits to Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduce except in full, without prior written approval of the Company. Any unauthorized alternion, forgery or falsification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



No.: QDIN2206003832SC

Date: Jul 06, 2022

Page: 3 of 4

Test Item: Neutral Salt Spray Test Sample Description: See photo Test Method: ISO 9227:2017

Test Condition:

Concentration of solution collected: (50±5)g/L NaCl

Chamber temperature: (35±2)°C

Volume of salt solution collected: (1.5±0.5) ml/(80cm²·h)

pH of collected solution at (25±2) °C: 6.5~7.2

Exposure period: 48h

Test Result:

Test Item	Appearance rating	Client's requirement	Conclusion
Neutral Salt Spray Test	10	Appearance rating: 10	Pass

Note:

1. Appearance rating refers to ISO 10289:1999, as follows:

Area of defects, A (%)	Appearance rating	
0(No defects)	10	
0 <a≤0.1< td=""><td>9</td></a≤0.1<>	9	
0.1 <a≤0.25< td=""><td>8</td></a≤0.25<>	8	
0.25 <a≤0.5< td=""><td>7</td></a≤0.5<>	7	
0.5 <a≤1.0< td=""><td>6</td></a≤1.0<>	6	
1.0 <a≤2.5< td=""><td>5</td></a≤2.5<>	5	
2.5 <a≤5.0< td=""><td>4</td></a≤5.0<>	4	
5.0 <a≤10< td=""><td>3</td></a≤10<>	3	
10 <a≤25< td=""><td>2</td></a≤25<>	2	
25 <a≤50< td=""><td>1</td></a≤50<>	1	
50 <a< td=""><td>0</td></a<>	0	

2. Defects of edge and mounting holes do not influence the numerical rating.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspy and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of his document sadvised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits to client's instructions, if any. The Company's soft eresponsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

SGS Center, No. 143, Zhuzhou Road, Laoshan District, Qingdao, China 266101 t (86–532) 68999888 f (86–532) 80991955




No.: QDIN2206003832SC

Date: Jul 06, 2022

Page: 4 of 4

Test Photo:



Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Corrosion Test	SSP 1100	POL-AG-E045	2022.05.13	2023.05.12
Apparatus				

******* End of report******



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="https://www.sgs.com/en/Terms-and-Conditions/Terms-and-C